



Sintergewebe	Bezeichnung	Geometrische Porengrösse	Dicke	Porösität	Druckverlust	As	Rp	Gewicht	spez. Durchfluss-Kennzahl
		μm	mm	%	mbar	mm^2 / cm	N / cm	kg / m^2	Eu
Poremet	Poremet 2	10	1.7	30	6.8	5.1	1080	9.5	5146
	Poremet 5	14	1.7	30	5	5.1	1080	10	3784
	Poremet 10	21	1.7	30	3.1	5.1	1080	10	2346
	Poremet 15	20	1.7	30	2.05	5.1	1080	9.5	1551
	Poremet 20	25	1.7	30	1.91	5.1	1080	9.5	1446
	Poremet 30	35	1.7	30	1.69	5.1	1080	9.5	1279
	Poremet 40	50	1.7	30	1.54	5.1	1080	9.5	1166
	Poremet 50	60	1.7	30	1.43	5.1	1080	10	1082
	Poremet 60	75	1.7	30	1.34	5.1	1080	10	1014
	Poremet 75	90	1.7	30	0.56	5.1	1080	10	424

Version: 01.05.2015